

**PRODUCT: PEL FZ 299**

**PRODUCT DESCRIPTION:** PEL-FZ-299 is an LLDPE blown film grade of PolyEarthylene® with a biobased content of about 50%. It is designed as a shrink film meant to be processed with PEL-FL-297. All data presented has been analyzed in accordance with ASTM standards. This material is FDA Title-21 Food Contact Compliant. The biodegradation timeline for this material in film form is approximately 1-3 years.

Renewable Content	
Biobased Content (%) (ASTM D6866)	~50%

CHARACTERISTIC	TEST METHOD	VALUE	UNIT
MELT FLOW INDEX	ASTM D1238 Procedure A	0.85	g/10 min (190°C, 2.16Kg)
SPECIFIC GRAVITY	ASTM D792	0.928	g/cm³
HARDNESS (SHORE D)	ASTM D2240	57	N/A
TENSILE STRENGTH (@YIELD)	ASTM D638	1835	psi
TENSILE STRENGTH (@BREAK)	ASTM D638	1660	psi
TENSILE MODULUS	ASTM D638	26880	psi
TENSILE ELONGATION	ASTM D638	630	%
FLEXURAL MODULUS	ASTM D790	18894	psi
FLEXURAL STRENGTH	ASTM D790	1035	psi
IZOD IMPACT STRENGTH (NOTCH 1/8" SPECIMEN)	ASTM D256	5.96	Ft-lb/in (73 °F)

**Processing Conditions:**

PolyEarthylene® resins can be processed with conventional blown film equipment. The addition of this resin should be performed after a standard purging process. The melt temperature of the resin should be kept below 450 °F, if possible.

Manufacturing processes differ and the temperature ranges for blown film extrusion presented in the table are only suggested by Verde Bioresins, Inc.®

Modifications to operational parameters may be required for some equipment. Any questions related to the material can be addressed to Verde Bioresins, Inc.®

**Packaging and Storing:**

This resin is packaged in a sealed, foil lined gaylord or bag. The product should be stored in a cool, dry, and isolated area away from moisture and other contaminants to achieve maximum stability and performance.

**Extrusion:**

Description of Temperature Zone	Temperatures (Range Value)
Feed	100-200°F
Barrel	330-390°F
Die Head	330-390°F

**Notes:**

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by the molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed. This data is not based on the minimum quantity of results required to report as qualifying specifications and may be subject to refinement. Data herein is typical and not to be construed as specifications.