

**POLYEARTHYLENE
TECHNICAL DATA SHEET**



PRODUCT: PEL FZ 343

Renewable Content	
Biobased Content (%) (ASTM D6866)	>45%

PRODUCT DESCRIPTION: PEL FZ 343 is a biobased and biodegradable cast film grade of PolyEarthylene tailored specifically for the core layer of stretch film applications. All data presented has been analyzed in accordance with ASTM standards. No BPAs, phthalates, and PFAs added. The biodegradation timeline for this resin is approximately 1-3 years.

CHARACTERISTIC	TEST METHOD	VALUE	UNIT
MELT FLOW INDEX	ASTM D1238 Procedure A	2.77	g/10 min (190°C, 2.16Kg)
SPECIFIC GRAVITY	ASTM D792	0.917	g/cm ³
HARDNESS (SHORE D)	ASTM D2240	69	N/A
NOTCHED IZOD IMPACT	ASTM D256	6.53	Ft-lb/in (73 °F)
TENSILE STRENGTH (@YIELD)	ASTM D638	2,142	psi
TENSILE STRENGTH (@BREAK)	ASTM D638	2,011	psi
TENSILE MODULUS	ASTM D638	15,712	psi
TENSILE ELONGATION	ASTM D638	937	%
FLEXURAL MODULUS	ASTM D790	15,290	psi
FLEXURAL STRENGTH	ASTM D790	917	psi

Molding Conditions:

PolyEarthylene resins can be processed with conventional cast film equipment. The addition of this resin should be performed after a standard purging process. The melt temperature of the resin should be kept below 450°F if possible.

Every manufacturing process is different and the temperature ranges for cast film extrusion presented in the table are only suggested by Verde Bioresins, Inc.

Modifications to operational parameters may be required for some equipment. Any questions related to the material can be addressed to Verde Bioresins, Inc.

Description of Temperature Zone	Temperatures (Range Value)
Feed	100-200°F
Barrel	340-450°F
Die	340-450°F

Packaging and Storing:

This resin is packaged in a sealed, foil lined gaylord or bag. The product should be stored in a cool, dry, and isolated area away from moisture and other contaminants to achieve maximum stability and performance.

Notes:

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by the molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed. This data is not based on the minimum quantity of results required to report as qualifying specifications and may be subject to refinement. Data herein is typical and not to be construed as specifications.