PolyEarthylene®

Verde®

Technical Data Sheet

PEL FL 297

Product Description

An LDPE grade of PolyEarthylene® with a minimum biobased content of 30%. It is a blown film grade of PolyEarthylene® designed to be processed with PEL-FZ-299 to create shrink film.

Renewable Content	
Minimum Biobased Content (%) (ASTM D6866)	30%
Est. Biodegradation Timeline (Years)	3-5

General

- Complies with U.S. FDA 21 CFR 177.1520 (c)3.1a
- No BPAs, phthalates, or PFAS intentionally added
- Recyclable
- Biodegrades in a landfill environment in 3-5 years under ASTM D5511

Properties	Value (English)	Value (SI)	Method
Melt Flow Index (190°C, 2.16 kg)	0.21 g/10min	0.21 g/10min	ASTM D1238 Procedure A
Specific Gravity	0.924	0.924	ASTM D792
Durometer Hardness (Shore D)	55	55	ASTM D2240
Tensile Strength @Yield	1,705 psi	11.7 MPa	ASTM D638
Tensile Strength @Break	1,573 psi	10.8 MPa	ASTM D638
Tensile Modulus	28,079 psi	193 MPa	ASTM D638
Tensile Elongation	67.1 %	67.1 %	ASTM D638
Flexural Modulus	13,054 psi	90 MPa	ASTM D790
Flexural Strength @Peak	723 psi	4.9 MPa	ASTM D790
1/8” Notch Izod Impact Strength (73 °F)	5.56 ft-lb/in	297 J/m	ASTM D256

Processing Conditions:

PolyEarthylene resins can be processed with conventional blown film equipment. The addition of this resin should be performed after a standard purging process. The melt temperature of the resin should be kept below 390°F, if possible.

.

Manufacturing processes differ and the temperature ranges for blown film presented in the table are only suggested by Verde Bioresins, Inc.

Modifications to operational parameters may be required for some equipment. Any questions related to the material can be addressed to Verde Bioresins, Inc.

Blown Film Processing Parameters:

Description of Temperature Zone	Temperatures (Range Value)
Feed	100-200°F
Barrel	330-390°F
Die Head	330-390°F

Disclaimer:

All data present has been analyzed in accordance with ASTM standards. Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by the molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed. This data is not based on the minimum quantity of results required to report as qualifying specifications and may be subject to refinement. Data is typical and not to be construed as specifications.

Living Document
Revision 6
Revision Date: 09/03/2026

DCR: 233
Effective Date: 09/03/2026